



مصنع رأس الخيمة
للمواد اللاصقة والعازلة راكم ش.ذ.م
RAS AL KHAIMAH
ADHESIVE & WATERPROOF MATERIALS FACTORY RAKAM LLC



503 - RAK WALL PUTTY

معجونة ستوكو داخلية (Interior Stucco Putty)



معجونة ستوكو داخلية (Interior Stucco Putty)

اندرونی اسٹوکو پٹی

ഇന്റീരിയർ സ്റ്റൂക്കോ പുട്ടി

P.O. BOX 11005, RAS AL KHAIMAH - U.A.E

sales@rakam.ae www.rakam.ae

+9717 266 8383 +9717 266 8853





RAKAM

TECHNICAL DATA SHEET

503 RAK WALL PUTTY

(Interior Stucco Putty) معجونة ستوكو داخلية

A poly-vinyl acetate ready mixed putty, designed for filling minor cracks, small dents, voids, air-holes and eliminating surface imperfections, recommended for use on interior concrete and plaster surfaces, to give a fine and smooth surface.

MAIN FEATUURES	INSTRUCTION FOR USE	HEALTH & SAFETY																
<ul style="list-style-type: none"> • Can be applied directly on to the surface. • Ease of application. • Easy to sand when dry. • Non-sagging properties at high film thickness. • Excellent filling properties. • Good adhesive strength. 	<p>Tools Spatula, Trowel or Putty Knife.</p> <p>Thinner No thinning required (ready for use)</p>	<p>Protective clothing such as gloves and goggles should be worn when handling the product. Treat any splashes to the skin or eyes with fresh water immediately. Should any of the products be accidental swallowed, do not induce vomiting, but call for medical assistance immediately. Ensure that the container is available for medical attendant to examine any relevant instructions and content details.</p>																
	<p>SUBSEQUENT COATS</p> <p>RAKAM Primer Sealer RAKAM Undercoat</p>																	
<p>SURFACE PREPARATION</p> <p>The surface should be sound, dry and clean, free from dirt, oil, grease, and loose paint, or powdery material.</p>	<p>COLOUR</p> <p>White</p>																	
<p>NEW SURFACES</p> <ol style="list-style-type: none"> 1. Sand the surface until completely smooth, removes all the dust. 2. If the surface is too much dry, the surface should be wetted with clean water. 3. Apply one coat of RAK Primer Sealer or RAK Latex Sealer, if the surface is too much porous. 4. Apply 1-2 Coats of RAK Wall Putty. 5. After drying, sand the putty and clean the surface. 	<p>PACKING</p> <p>28 Kg./drum , 5 Kg./gallon</p>		<p>REMARKS</p> <ul style="list-style-type: none"> • Stir well before use... • Avoid application below 5 °C or over 85% relative humidity. • After using, clean the application tools immediately with water. • Close container after use. • Store in a cool and dry place. • Keep out of reach of children. • For more information, please do not hesitate to contact our Technical Department. 															
	<p>PHYSICAL SPECIFICATION</p> <table> <tr> <td>- Specific gravity</td> <td>Approx. 1.75 g/cc</td> </tr> <tr> <td>- Solid by weight</td> <td>Approx. 72%</td> </tr> <tr> <td>- Coverage rate</td> <td>0.5 – 1.0 Kg/ M² depending on surface condition</td> </tr> <tr> <td>- Dry film thickness</td> <td>max 1 mm</td> </tr> <tr> <td>- Shelf life</td> <td>1 Year</td> </tr> <tr> <td>- Flash point</td> <td>Not applicable</td> </tr> <tr> <td>- Finish</td> <td>Matt</td> </tr> <tr> <td>- Drying time at 25 °C</td> <td>Surface dry approx. 1 hour Hard dry approx. 2 hours</td> </tr> </table> <p>* Next coat can be applied after 4 hours...</p>	- Specific gravity	Approx. 1.75 g/cc	- Solid by weight	Approx. 72%	- Coverage rate	0.5 – 1.0 Kg/ M ² depending on surface condition	- Dry film thickness	max 1 mm	- Shelf life	1 Year	- Flash point	Not applicable	- Finish	Matt	- Drying time at 25 °C	Surface dry approx. 1 hour Hard dry approx. 2 hours	
- Specific gravity	Approx. 1.75 g/cc																	
- Solid by weight	Approx. 72%																	
- Coverage rate	0.5 – 1.0 Kg/ M ² depending on surface condition																	
- Dry film thickness	max 1 mm																	
- Shelf life	1 Year																	
- Flash point	Not applicable																	
- Finish	Matt																	
- Drying time at 25 °C	Surface dry approx. 1 hour Hard dry approx. 2 hours																	

